

(A 01) Via Bresciani, 16 46040 Gazoldo degli Ippoliti Mantova Italy
 Tel. +39 - 0376 685 1 www.marcegaglia.com

Stabilimento di Contino: Via Aido, 3, 46049 Volta Mantovana MN Tel. +39
 0376 84601

CUSTOMER DATA AND DELIVERY

(A 06.1) CUSTOMER: **KROKAR D.O.O. (0000012339)** **Jesenice**
 (A 06.2) CONSIGNEE: **KROKAR D.O.O. (0000012339)** **Jesenice**
 (A 10) Delivery Number: **8930824414** (A 11) Shipping Notice: **1002009741** of **11/11/2025**

ORDER DATA

(A 08) Marcegaglia Order Number: **1191956665/000010**
 (A 07) Customer Order Number: **107-NAR-25-1049**
 (A 07) Date Of Order Confirmation To The Customer: **05/11/2025**

PRODUCT IDENTIFICATION

(B 01) Material Code: **55002422**
 (B 09) Material Description: **TRT 22,00x6000 S235JRC TRAF**
 (B 10) Material Description: **COLD DRAWN ROUND Toll h9 EN 10277**
 (B 02) Steel Grade: **S235JRC S235B**
 (B 03) Manufacturing Standard: **EN10277 ISO 683-7**
 (B 14) Welding Technology:

SUPPLIED BATCH CHARACTERISTICS

| ITEM | (B 07) BATCH NUMBER | (B 20) HEAT NUMBER | (B12) KG |
|------|---------------------|--------------------|----------|
| 1 | 25QU505634 | 3120220 | 1006 |
| 2 | 25QU505635 | 3120220 | 1007 |
| 3 | 25QU505636 | 3120220 | 1004 |

CHEMICAL ANALYSIS

The chemical analysis refers to the raw material used. In accordance with EN 10204:2004 the values of the chemical analysis, unless otherwise specified, refer to the 3.1 type certificate of the raw material supplier.

| ITEM | (B 07) BATCH NUMBER | (B 20) HEAT NUMBER | (C 71) C (%) | (C 72) Si (%) | (C 73) Mn (%) | (C 74) P (%) | (C 75) S (%) | (C 76) N (%) | (C 83) Cu (%) |
|------|---------------------|--------------------|--------------|---------------|---------------|--------------|--------------|--------------|---------------|
| | MIN | | | | | | | | |
| | MAX | | | | | | | | |
| 1 | 25QU505634 | 3120220 | 0.096 | 0.197 | 0.679 | 0.0125 | 0.0090 | 0.0090 | 0.246 |
| 2 | 25QU505635 | 3120220 | 0.096 | 0.197 | 0.679 | 0.0125 | 0.0090 | 0.0090 | 0.246 |
| 3 | 25QU505636 | 3120220 | 0.096 | 0.197 | 0.679 | 0.0125 | 0.0090 | 0.0090 | 0.246 |

MECHANICAL PROPERTIES

| TENSILE TEST (C 03) AT ROOM TEMPERATURE t = (22 ± 4)°C | | | | | | | |
|--|---------------------|------------------------|-------------------|---------------------|--------------|-----------------|--------------|
| ITEM | (B 07) BATCH NUMBER | (C 01) SAMPLE POSITION | (C 02) SAMP. DIR. | (C 11) Rp 0.2 (MPa) | (C 11) (MPa) | (C 12) Rm (MPa) | (C 13) A (%) |
| | MIN | | | | | | |
| | MAX | | | | | | |
| 1 | 25QU505634 | CAMP1 | L | 489 | | 580 | 17.4 |
| 2 | 25QU505635 | CAMP1 | L | 489 | | 580 | 17.4 |
| 3 | 25QU505636 | CAMP1 | L | 489 | | 580 | 17.4 |

Test Position: B=Coil Tail, C=Coil Centre, T=Coil Head
 Test Direction: T=Transversal Sense, L=Longitudinal Sense

(D 94) NOTE

- WE CERTIFY THAT MATERIAL SUPPLIED COMPLIES WITH THE REQUIREMENTS AGREED ON ORDER

CERTIFICATE VALIDATION



(A 02) INSPECTION CERTIFICATE 3.1 EN 10204
ACCORDING TO EN 10204:2004 ALPHANUMERIC CODES ACCORDING TO EN
10168:2004
(A 03) Certificate Number 10225718716
(Z 02) Issue Date 11/11/2025

(Z 02) The present test certificate is validated by **A. Dal Prato** - Quality Manager,
Marcegaglia Specialties Volta Mantovana Plant authorized inspection representative,
independent of the manufacturing department

A handwritten signature in black ink, appearing to read 'A. Dal Prato'.

(Z 01) Statement of Compliance: WE CERTIFY THAT THE ABOVE MENTIONED
PRODUCTS COMPLY WITH THE TERMS OF ORDER CONTRACT AND THE
STANDARDS RECALLED IN THE PRESENT TEST CERTIFICATE